
STANCHEM SC 6153

DESCRIPTION:

StanChem SC 6153 is a high Tg, heat reactive acrylic copolymer emulsion that exhibits excellent UV resistance, good solvent resistance and good pigment binding.

PRODUCT DATA: Typical Physical Properties:

Type:	Acrylic Polymer Emulsion
Solids by weight:	39.0 – 41.0 %
Viscosity @ 25 °C: Brookfield RVT 2 @ 40 Rpm	< 1000 cps
pH @ 25° C:	6.5 – 7.5
Tg (DSC midpoint)	63°C

Storage: SC 6153 is stable for at least 12 months from manufacturing date when stored at +5C to +40C in appropriate containers.

WARRANTY:

Seller warrants that its product will meet the specifications which it sets for them. Seller's responsibility under this warranty will be limited solely to replacing the products which prove defective, provided that the Buyer gives Seller prompt notice in writing of said defect. Products may be returned to Seller only after written authorization has been obtained from Seller. The foregoing warranty is in lieu of all other warranties, whether oral, written, express, implied or statutory. IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE WILL NOT APPLY. Technical or other advice is furnished by us solely as an accommodation and shall not increase the scope of our responsibilities or liability. Seller's warranty obligations and Buyer's remedies hereunder are solely and exclusively as stated herein: In no event will Seller be liable either for the labor and other associated costs incurred in replacing the product, including, but not limited to, its removal and application, or for other incidental or consequential damages.