
STANCHEM SC 6749

DESCRIPTION:

StanChem SC 6749 is a low Tg, flexible all acrylic polymer designed for coatings, inks and colorants. SC 6749 provides flexibility in compounding with other acrylics or polyurethanes. SC 6749 is APEO free and formaldehyde free.

PRODUCT DATA: Typical Physical Properties:

Type:	Acrylic Copolymer Emulsion
Solids by weight:	39.0 – 41.0 %
Viscosity @ 25° C: Brookfield RVT 4 @ 20 Rpm	<300 cps
pH @ 25°C:	8.0 – 9.0
Free Monomer:	0.1 % maximum
Weight/gallon:	8.8 +/- 0.1 lbs./gal
Tg° C	- 20

Storage: SC 6749 is stable for at least 12 months from manufacturing date when stored at +5C to +40C in appropriate containers.

WARRANTY:

Seller warrants that its product will meet the specifications which it sets for them. Seller's responsibility under this warranty will be limited solely to replacing the products which prove defective, provided that the Buyer gives Seller prompt notice in writing of said defect. Products may be returned to Seller only after written authorization has been obtained from Seller. The foregoing warranty is in lieu of all other warranties, whether oral, written, express, implied or statutory. **IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE WILL NOT APPLY.** Technical or other advice is furnished by us solely as an accommodation and shall not increase the scope of our responsibilities or liability. Seller's warranty obligations and Buyer's remedies hereunder are solely and exclusively as stated herein: In no event will Seller be liable either for the labor and other associated costs incurred in replacing the product, including, but not limited to, its removal and application, or for other incidental or consequential damages.